



LEMBAGA GETAH MALAYSIA

Malaysian Rubber Board

RUBBER RESEARCH INSTITUTE OF MALAYSIA PHYSICAL TESTING LABORATORY

Rubber Technology Centre, RRIM Research Station, 47000 Sungai Buloh, Selangor Darul Ehsan.
Main Line Tel: (6)03-61561121 Fax: (6)03-61564418
Tel: (6)03-61576748 Fax: (6)03-61563304
E-mail: ptl@lgm.gov.my



MS ISO / IEC 17025
TESTING / CALIBRATION
SAMM NO.008

PAGE : 2 of 2

TEST REPORT

REPORT NO : QA/2009/0341/4

DATE : 17/04/2009

Sample Description : Testing On Tensile Strength Of Brand – Sanctband (Bands)

Marked : Type of Sample Colour(s) Size
4) Sanctband Blue (Lot No.: 071208) 0.30mm x 15cm x 1.5m

Test to Standard : ASTM D412

Date of Testing : 15/04/2009 To 16/04/2009

Tensile Properties Unaged

Sample Reference	Customer Reference	Tensile Strength (Kgf)	Elongation at Break, (%)	Modulus at 100% (Kgf)	Modulus at 200% (Kgf)	Modulus at 300% (Kgf)
QA/2009/0341/4.01	Blue	350.5	760	9.9	14.1	18.4

Tensile Properties Unaged

Sample Reference	Customer Reference	Tensile Strength (MPa)	Elongation at Break, (%)	Modulus at 100% (MPa)	Modulus at 200% (MPa)	Modulus at 300% (MPa)
QA/2009/0341/4.01	Blue	34.4	760	1.0	1.4	1.8

Norlee Ramli
Research Officer
Physical Testing Laboratory
for Director General MRB

