




LEMBAGA GETAH MALAYSIA
MALYSIAN RUBBER BOARD
RUBBER RESEARCH INSTITUTE OF MALAYSIA

Unit Pencirian Bahan
260 Jalan Ampang, 50450 Kuala Lumpur.
Peti Surat 10150, 50908 Kuala Lumpur, Malaysia.
Tel: (6)03-92062000, 92063681 Fax: (6)03-42519213
Email: kartinia@lgm.gov.my



MS ISO/IEC 17025
TESTING
SAMM NO.069



April 16, 2009

Our report no : LGM/BTK/UPB/5.10/CP/0904/0658-0663

SANCTUARY HEALTH SDN. BHD.
No. 464, Jalan Kuala Kangsar,
30100 Ipoh,
Perak Darul Ridzuan.

Fax: 605-2921739

E-mail: info@sanctuaryhealth.com.my

(Attention: Chang Chaur Long)

EXTRACTABLE PROTEIN CONTENT

We have received samples delivered to us under your covering letter dated 03/04/2009. Analysis had been carried out as per your request. We report the following results:

Date of receipt of sample	13/04/2009
Date tested	15/04/2009
Test Method	ASTM D5712 – 2005
Sample Condition	Unaged
Type of sample	Sanctband (Tubing)

Sample Reference	Protein Content ($\mu\text{g/g}$)
6. Lot No. : 080408 Colour : Silver	<50

The sensitivity limit of the method is 50 $\mu\text{g/g}$

Kartini Alias
Research Officer
Material Characterization Unit
Malaysian Rubber Board
For Director General