



LEMBAGA GETAH MALAYSIA

Malaysian Rubber Board

RUBBER RESEARCH INSTITUTE OF MALAYSIA

PHYSICAL TESTING LABORATORY

Rubber Technology Centre, RRIM Research Station, 47000 Sungai Buloh, Selangor Darul Ehsan.

Main Line Tel: (6)03-61561121 Fax: (6)03-61564418

Tel: (6)03-61576748 Fax: (6)03-61563304

E-mail: ptl@lgm.gov.my



MS ISO / IEC 17025

TESTING / CALIBRATION
SAMM NO.008

PAGE : 2 of 2

TEST REPORT

REPORT NO : QA/2009/0342/4

DATE : 17/04/2009

Sample Description : Testing On Tensile Strength Of Brand – Sanctband (Tubing)

Marked : Type of Sample Colour(s) Size
4) Sanctband Blue (Lot No.: 090608) 6.5mm x 2.5mm x 1.2m

Test to Standard : ASTM D412

Date of Testing : 15/04/2009 To 16/04/2009

Tensile Properties Unaged

Sample Reference	Customer Reference	Tensile Strength (Kgf)	Elongation at Break, (%)	Modulus at 100% (Kgf)	Modulus at 200% (Kgf)	Modulus at 300% (Kgf)
QA/2009/0342/4.01	Blue	253.1	790	7.1	10.3	13.7

Tensile Properties Unaged

Sample Reference	Customer Reference	Tensile Strength (MPa)	Elongation at Break, (%)	Modulus at 100% (MPa)	Modulus at 200% (MPa)	Modulus at 300% (MPa)
QA/2009/0342/4.01	Blue	24.8	790	0.7	1.0	1.3

Norlee Ramli
Research Officer
Physical Testing Laboratory
for Director General MRB

