



LEMBAGA GETAH MALAYSIA

Malaysian Rubber Board

RUBBER RESEARCH INSTITUTE OF MALAYSIA PHYSICAL TESTING LABORATORY

Rubber Technology Centre, RRM Research Station, 47000 Sungai Buloh, Selangor Darul Ehsan.

Main Line Tel: (6)03-61561121 Fax: (6)03-61564418

Tel: (6)03-61576748 Fax: (6)03-61563304

E-mail: ptl@lgm.gov.my



MS ISO / IEC 17025

TESTING / CALIBRATION
SAMM NO.008

PAGE : 2 of 2

TEST REPORT

REPORT NO : QA/2009/0342/2

DATE : 17/04/2009

Sample Description : Testing On Tensile Strength Of Brand – Sanctband (Tubing)

Marked : Type of Sample Colour(s) Size
2) Sanctband Orange (Lot No.: 131208) 6.5mm x 1.7mm x 1.2m

Test to Standard : ASTM D412

Date of Testing : 15/04/2009 To 16/04/2009

Tensile Properties Unaged

Sample Reference	Customer Reference	Tensile Strength (Kgf)	Elongation at Break, (%)	Modulus at 100% (Kgf)	Modulus at 200% (Kgf)	Modulus at 300% (Kgf)
QA/2009/0342/2.01	Orange	261.2	780	8.2	12.0	16.2

Tensile Properties Unaged

Sample Reference	Customer Reference	Tensile Strength (MPa)	Elongation at Break, (%)	Modulus at 100% (MPa)	Modulus at 200% (MPa)	Modulus at 300% (MPa)
QA/2009/0342/2.01	Orange	25.6	780	0.8	1.2	1.6

Norlee Ramli
Research Officer
Physical Testing Laboratory
for Director General MRB